



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C11D 17/00, 17/04		A1	(11) International Publication Number: WO 98/40464
			(43) International Publication Date: 17 September 1998 (17.09.98)
(21) International Application Number: PCT/EP98/01274		Unilever Research Lab, Lever Development Centre, Olivier van Noortlaan 120, NL-3133 AT Vlaardingen (NL).	
(22) International Filing Date: 24 February 1998 (24.02.98)		(74) Agent: MOLE, Peter, Geoffrey; Unilever plc, Patent Dept., Colworth House, Sharnbrook, Bedford MK44 1LQ (GB).	
(30) Priority Data: 9704776.5 7 March 1997 (07.03.97) GB		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).	
(71) Applicant (for AU BB CA GB GH GM IE IL KE LC LK LS MN MW NZ SD SG SI SZ TT UG ZW only): UNILEVER PLC [GB/GB]; Unilever House, Blackfriars, London EC4P 4BQ (GB).		Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(71) Applicant (for all designated States except AU BB CA GB GH GM IE IL KE LC LK LS MN MW NZ SD SG SL SZ TT UG US ZW): UNILEVER N.V. [NL/NL]; Weena 455, NL-3013 AL Rotterdam (NL).			
(72) Inventors; and (75) Inventors/Applicants (for US only): BOSKAMP, Jelles, Vincent [NL/NL]; Unilever Research Lab, Lever Development Centre, Olivier van Noortlaan 120, NL-3133 AT Vlaardingen (NL). COLE, Andrew [GB/GB]; Lever Brothers Ltd., Port Sunlight, Wirral, P.O. Box 69, Merseyside L62 4ZD (GB). KERR, Colin, Watt [GB/GB]; Lever Brothers Ltd., Port Sunlight, Wirral, P.O. Box 69, Merseyside L62 4ZD (GB). LEMPERS, Edwin, Leo, Mario [NL/NL];			
(54) Title: DETERGENT-PACKAGE COMBINATION			
(57) Abstract			
<p>A combination comprises at least one tablet of compacted particulate detergent composition, stored for at least 24 hours, within a packaging system having a moisture vapour transmission rate of less than 20 g/m²/24 hours. A process of preparing the combination is disclosed.</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

- 1 -

DETERGENT - PACKAGE COMBINATIONIntroduction

5 The invention relates to a detergent package combination,
and in particular to a detergent tablet - package
combination.

10 One of the most prominent problems associated with
detergent tablets is the provision of a tablet which is
sufficiently strong to withstand processing, packaging,
transport and handling without breaking or chipping, yet
still be able to disintegrate quickly in an aqueous
environment.

15 Detergent - package combinations are described in, for
example, WO95 02681, which relates to a combination of a
granular detergent composition which is contained in a
packaging system having a moisture vapour transmission
20 rate, hereinafter MVTR, of less than 20 g/m²/24 hours.

WO 95/18215 describes a detergent article comprising a
detergent mass of at least 100 g, typically 2 Kg to 5 Kg,
having a barrier layer coating to prevent absorption of
25 water. The teaching of this document is directed towards
cast blocks of detergent material which, if unprotected,
absorb large quantities of water rendering the blocks
soft and malleable.

30 The present invention is directed towards the provision
of an improved detergent-package combination which
provides improved physical and functional

- 2 -

characteristics, for the detergent contained within the package.

Statement of Invention

5

According to the invention, there is provided a combination of at least one tablet of compacted particulate detergent composition stored for at least 24 hours within a closed packaging system having a moisture vapour transmission rate of less than $20\text{g/m}^2/24$ hours.

10

15

Surprisingly, it has been found that the above combination, when stored, results in a detergent tablet having improved physical characteristics, that is to say, the physical strength of the tablet increases considerably upon storage. This is a surprising and unexpected result. Even more surprising is the observation that, while the physical strength of the tablets increased, the dissolution time of the tablets in water actually decreases. Furthermore, the functional characteristics of the tablets have been found to be excellent.

20

25

Generally, the MVTR of the packaging system is less than $10\text{ g/m}^2/24$ hours, ideally approximately $5\text{ g/m}^2/24$ hours.

30

In a preferred embodiment of the invention, the detergent composition comprises either (a) a sodium tri-polyphosphate composition, or (b) a sodium acetate trihydrate composition optionally together with sodium citrate dihydrate. These components have been found to be highly effective disintegrants which, while allowing the tablets to be compressed to produce a tablet of

- 3 -

increased strength, allow a rapid disintegration of the tablet in water. Ideally, the detergent composition comprises phase I sodium tripolyphosphate which has been found to be a particularly effective disintegrant.

5

In a particularly preferred embodiment of the invention, the detergent composition comprises at least one tablet of a compacted particulate composition wherein the tablet or a region thereof comprises from 2% to 35% by weight of a salt which is sodium acetate trihydrate, potassium acetate or mixture thereof, optionally together with sodium citrate dihydrate, such that the total quantity of sodium acetate trihydrate, potassium acetate and sodium citrate dihydrate is from 7% to 50% by weight of the tablet or region thereof. Optionally the tablet may contain 15% to 93% of a water softening agent.

10

15

20

25

30

Alternatively, the detergent composition comprises a tablet of compacted particulate detergent composition, containing one or more detergent-active compounds together with sodium tripolyphosphate and other ingredients, characterised in that the tablet or a region thereof comprises particles which contain sodium tripolyphosphate with a content of the phase I form which is more than 40% by weight of the sodium tripolyphosphate in the particles, wherein the sodium tripolyphosphate in said particles contains water of hydration distributed throughout the tripolyphosphate in an amount between 1% and 5% by weight of the sodium tripolyphosphate in the particles. Ideally the detergent composition is stored in the packaging system for at least 1 week, preferably at least 2 weeks, more preferably at least 3 weeks, ideally at least 4 weeks. In one particularly preferred

- 4 -

embodiment of the invention the packaged detergent composition is stored for up to 8 weeks, and often for even greater than 8 weeks.

5 The packaging system will advantageously have a reasonable oxygen permeability, ideally not greater than 2000 cm³/m³/24 hours.

10 Typically, the packaging system comprises a material having a bulk density of less than 40g/m².

Ideally, the packaging system comprises a polymeric film, preferably an oriented polypropylene film. Suitable films are sold under the trademark BICOR.

15 Alternatively, the packaging system may comprise a PET/PE laminate, preferably having a thickness of approximately 12 micron PET/40 micron PE.

20 In a preferred embodiment of the invention the detergent composition, is wrapped in a flow-wrap sealed polymer-based packaging system such as those described above.

25 Suitable packaging systems are the films sold under the trade name BICOR having the following codes:- MB 668, MB 666, MB 600, MB 450, MB 400, MD 447, MH 648, MW 648, MH 647 and MW 647.

30 The invention also provides a process for preparing a packaged detergent composition comprising the steps of:-

- 5 -

- placing at least one tablet of compacted particulate detergent composition in a packaging system having a MVTR of less than 20 g/m²/24 hours;

5 - sealing the packaging system; and

- storing the thus formed sealed packaged detergent composition for at least 24 hours.

10 In one embodiment of the invention, the tablets comprise particulate detergent composition compacted with a force of at least 3N, typically greater than 4N, ideally greater than 5N and most preferably greater than 6N.

15 Ideally, a ratio of the DFS (KPa) to the T₉₀(mins) for the tablets is greater than 1, ideally greater than 2.

Detailed Description

20 The invention will be more clearly understood from the following description of some embodiments thereof given by way of example only.

Example 1

25 In this example of the invention, the combination comprises two sodium tripolyphosphate containing detergent tablets flow wrapped in sealed oriented polypropylene wrapping of the type sold under the trade
30 mark BICOR MB 668.30, and stored for different periods of time under specific conditions of temperature and humidity.

- 6 -

A. Detergent Tablet Details

The composition and manufacture of the tablets is given below.

Tablets for use in fabric washing were made, starting with a spray-dried base powder of the following composition:

Sodium linear alkylbenzene sulphonate	11.83%
Sodium tripolyphosphate, type 1A ¹	44.83%
Nonionic detergent ²	7.88%
Sodium silicate	11.83%
Soap	1.13%
Sodium carboxymethyl cellulose	0.9%
Acrylate/maleate copolymer	3.2%
Sodium sulphate and minor ingredients	3.0%
Water	balance to 100%

¹ This contained less than 30% of the phase I form of anhydrous sodium tripolyphosphate.

² C₁₃₋₁₅ fatty alcohol 7EO.

- 7 -

This powder was mixed with particles of sodium tripolyphosphate specified to contain 70% phase I form and contain 3.5% water hydration (Rhodia-Phos HPA 3.5 available from Rhone-Poulenc) and other detergent ingredients as tabulated below. As a comparative composition the base powder was mixed with urea and other detergent ingredients.

Two compositions thus contained the following percentages by weight.

	Example 1	Comparative A
Base Powder	63.25	63.25
Sodium perborate tetrahydrate	10.4	10.4
TAED granules	4.0	4.0
Anti-foam granule	2.0	2.0
Enzymes	0.85	0.85
Phosphonate	0.5	0.5
Sodium carbonate	3.6	3.6
HPA tripolyphosphate	15.0	---
Urea	---	15.0

35g portions of each composition were made into cylindrical tablets of 44mm diameter, using a Carver hand press.

- 8 -

B. Packaging Details

The packaging system comprised a sealed flow-wrap oriented polypropylene system sold under the trade mark BICOR MB 668.30. The properties of this material are given in Table 1.A below:-

Table 1.A

PROPERTIES	UNITS	MB 668			
		20	25	30	40
Tensile strength	N/mm ²	155	155	155	155
Modulus of Elasticity	N/mm ²	2200	2200	2200	2200
Breaking elongation	%	175	175	175	175
Coefficient of friction		0.25	0.25	0.25	0.25
Water vapour permeability	g/m ² /24 h	7.0	5.0	5.0	3.5
Oxygen permeability	cm ³ /m ² /24	1000	850	750	600
Haze	%	1.1	1.2	1.2	1.3
Gloss	%	85	85	85	85
Heat seal range	70	70	70	70	
Seal strength	g/25mm	400	400	400	400
Dimensional stability	%	-5	-5	-5	-5
Unit weight	g/m ²	18.2	22.7	28.2	37.3
Yield	m ² /kg	54.9	44.0	35.5	26.8

SUBSTITUTE SHEET (RULE 26)

- 9 -

C. Comparative Results

The improved physical and functional characteristics of tablets of the combination according to the invention were tested. Two sets of detergent tablets manufactured according to the protocol described above were stored under the same conditions of temperature and relative humidity (37°C/70% RH), one of the sets of tablets being left open to the environment (open conditions), the other being packaged and stored according to the invention in the material described above (closed conditions). The strength, dissolution characteristics and functional stability were measured at 0, 1, 2, 4 and 8 weeks for tablets stored under open and closed conditions. The results are given in Table 1.B below.

The strength of these tablets was measured using an Instron universal testing machine to compress a tablet until fracture. The value of diametral fracture stress (DFS) was then calculated using the equation.

$$\sigma = \frac{2P}{\pi Dt}$$

where σ is the diametral fracture stress in Pascals, P is the applied load in Newtons to cause fracture, D is the tablet diameter in metres and t is the tablet thickness in metres.

The break-up, dispersion and dissolution of tablets was measured by a test procedure in which a tablet is placed on a plastic sieve with 2 mm mesh size which was immersed in 9 litres of demineralised water at ambient temperature

- 10 -

of 22°C and rotated at 200 rpm. The water conductivity was monitored until it reached a constant value.

The time for break up and dispersion of the tables was taken as the time (T_{90}) for change in the water conductivity to reach 90% of its final magnitude. This was also confirmed by visual observation of the material remaining on the rotating sieve.

10

- 11 -

Table 1.B

Time	DFS (KPa) Closed Conditions	DFS (KPa) Open Conditions	Dissolution (T ₉₀) Closed Conditions	Dissolution (T ₉₀) Open Conditions	% Total TAED Closed Conditions	% Total TAED Open Conditions
0	9.9	9.9	4.7	4.7	100	100
1 Week	-	-	-	3.5	-	-
2 Week	15.9	12.7	3.4	2.4	100	-
4 Week	20.1	11.5	3.0	2.8	84	80
8 Week	24.6	-	3.2	-	80	-

- 12 -

Referring to Table 1B, it is clear that tablets stored under closed conditions increase in strength during the storage period. This effect is also observed in tablets stored under open conditions however to a much lesser degree. Indeed at 4 week storage, the measured DFS for tablets stored according to the invention is almost twice that of the comparative example.

The tablets stored under closed conditions dissolved faster the longer they are stored. This effect is also observed for tablets stored under open conditions, as would be expected. However, comparing the ratio of Tablet Straight (DFS) to Dissolution Time (T_{90}) for tablets stored for 4 weeks under open and closed conditions the following results are obtained.

DFS/ T_{90} for open conditions \approx 3.8

DFS/ T_{90} for closed conditions \approx 6.7

It is clear from these results that the tablet/packaging combination of the present invention results in a tablet of improved dissolvability and strength. The stability of the TAED is slightly better in the tablets packed and stores according to the invention. Overall, the results clearly demonstrate the improved physical and functional characteristics inherent in packing and storing tablets according to the invention.

Example 2

In this example, the same combination is used as that of example 1 with the exception that the detergent

- 13 -

composition comprises a sodium acetate trihydrate composition made according to the protocol below.

Detergent Tablets Details

5

Tablets for use in fabric washing were made, starting with a base powder of the following composition:

	Coconut alkyl sulphate ¹	2.9%
10	Zeolite A24 ²	52.9%
	Sodium carbonate	0.7%
	Nonionic detergent ³	25.9%
	Soap	5.9%
	Sodium carboxymethyl cellulose	1.4%
15	Fluorescer	0.4%
	Acrylate/maleate copolymer	0.7%

1. The coconut alkyl sulphate was incorporated as preformed granules containing 45% coconut alkyl sulphate, 35% zeolite, 11% sodium carbonate, balance water and other salts.

20

2. Maximum aluminium zeolite P from Crosfields.

25 3. C₁₃₋₁₅ fatty alcohol 7EO.

- 14 -

This powder was mixed with sodium acetate trihydrate (from Merck as used in Example 1) and other detergent ingredients as tabulated below. As a comparative composition the base powder was mixed with sodium citrate dihydrate and other detergent ingredients and then sprayed with polyethylene glycol (Molecular Weight 1500) at 80°C.

The two compositions thus contained:

	A (with Na-acetate 3aq). parts by weight	B (comparative) parts by weight
Base powder	53.02	53.02
Na-perborate 4aq.	19.99	19.99
TAED granules	4.49	4.49
Anti-foam granule	3.42	3.42
Enzymes	1.5	1.5
Phosphonate	1.0	1.0
Perfume	0.43	0.43
Na-acetate 3aq.	16.13	
Silicate-carbonate co-granule		5.5
Na-citrate 2aq.		8.03
PEG 1500		2.5

- 15 -

35g portions of each composition were made into cylindrical tablets of 44 mm diameter, using a Carver hand press with various levels of compaction force.

5 The strength of these tablets was measured using an Instron universal testing machine to compress a tablet until fracture. The value of diametral fracture stress (DFS) was then calculated using the equation

10
$$\diamond = \frac{2P}{\pi Dt}$$

where \diamond is the diametral fracture stress in Pascals, P is the applied load in Newtons to cause fracture, D is the tablet diameter in metres and t is the tablet thickness
15 in metres.

The break-up, and dispersion of tablets was measured by the procedure of Example 1, using one tablet on the rotating sieve.

- 16 -

The results are set out in the following table:

Compaction Force (kN)	A Tablets with Acetate.3H ₂ O		B Comparative tablets with citrate and PEG	
	Strength (DPS in kPa)	T ₉₀ (minutes)	Strength (DPS in kPa)	T ₉₀ (minutes)
1	5.1	4.0	--	--
2	7.2	3.8	19.3	11.1
4	13.7	3.9	31	25
5	20.8	7.5	43	30

It can be seen that the tablets containing acetate trihydrate, made with 5kN compaction force were almost equal in strength to the comparative tablets made at 2kN force, but dispersed faster and did not require a process step of spraying polymer onto the powder.

Comparative Test

Tablet manufactured according to the protocol above were stored and tested under the test conditions set out in Example 1.

The test results are given in Table 2.

- 17 -

Table 2.A

Time	DFS (KPa) Closed Conditions	DFS (KPa) Open Conditions	Dissolution (T ₉₀) Closed Conditions	Dissolution (T ₉₀) Open Conditions	% Total TAED Closed Conditions	% Total TAED Open Conditions
0	18.4	18.4	3.1	3.1	100	100
1 Week	19.5	10.0	3.1	5.0	95.6	43.4
2 Week	20.5	-	3.1	-	82.6	-
4 Week	18.3	-	2.8	-	91.3	-

- 18 -

Referring to Table 2B, and in particular to the figures on tablet strength, it is clear that tablets packed and stored according to the invention demonstrate an increase in strength over time when compared to the initial (T=0) measurements. This is not observed with tablets stored in open conditions. Comparing the dissolution times, as the strength of the tablets packed and stored according to the invention under closed conditions increases, the dissolution time remains relatively constant, and even decreases slightly after four weeks storage. The TAED stability of tablets packed and stored according to the invention is excellent.

Further tests were carried out on the tablets to measure the maximum load (F Max) the tablets can sustain and the energy required (Break Energy) to break the tablet. The tests were carried out on freshly made tablets and tablets stored for 1, 4 and 6 days according to the invention. The results are given in Table 2.B below:

Table 2.B

Time	F Max (N)	Break Energy (mJ)
T = 0	48.1	10.7
1 day	53.5	10.4
4 days	65.7	13.6
6 days	57.3	12.9

The above results clearly show that the tablet combination according to the invention, even when stored

- 19 -

for a period of 24 hours, results in tablets which are stronger than prior to storage.

5 The invention is not limited to the embodiments hereinbefore described which may be varied in both construction and detail.

- 20 -

CLAIMS

1. The combination of at least one tablet of compacted particulate detergent composition, stored for at
5 least 24 hours within a closed packaging system having a moisture vapour transmission rate of less than 20 g/m²/24 hours.
2. The combination of claim 1 in which the detergent
10 composition comprises a sodium tri-polyphosphate composition.
3. The combination of claim 1 in which the detergent
15 composition or a region thereof comprises particles whcih contain sodium tripolyphosphate with a content of the phase I form which is more than 40% by weight of the sodium tripolyphosphate in the said
20 particles, wherein the sodium tripolyphosphate in said particles contains water of hydration distributed throughout the tripolyphosphate in an amount between 1% and 5% by weight of the sodium tripolyphosphate in the particles.
4. The combination of claim 1 or 2 in which the
25 detergent composition comprises a sodium acetate trihydrate composition, optionally together with sodium citrate dihydrate.
5. The combination of claim 1 in which the detergent
30 composition or a region thereof comprising 15% to 93% by weight of a water-softening agent characterised in that the tablet or a region thereof

- 21 -

contains 2% to 35% by weight of a salt which is sodium acetate trihydrate, potassium acetate or mixture thereof, optionally together with sodium citrate dihydrate, such that the total quantity of sodium acetate trihydrate, potassium acetate and sodium citrate dihydrate is from 7% to 50% by weight of the tablet or region thereof.

6. The combination of any preceeding claim wherein the detergent composition is stored in the packaging system for at least 1 week.
7. The combination of any of claims 1 to 3 wherein the detergent composition is stored in the packaging system for at least 2 weeks.
8. The combination of any preceeding claim in which the packaging system has an oxygen permeability not more than $2000 \text{ cm}^3/\text{m}^2/24 \text{ hours}$.
9. The combination of any preceding claim in which the packaging system comprises a material housing a bulk density of less than 40 g/m^2 .
10. The combination of any preceding claim in which the packaging system comprises a polymeric film.
11. The combination as claimed in claim 10 in which the packaging system comprises an oriented polypropylene film.
12. The combination of any of claims 1 to 10 in which the polymeric film comprises a PET/PE laminate.

- 22 -

13. The combination of claim 12 in which the PET/PE laminate thickness is approximately 12 micron PET/40 PE.

5

14. The combination of any preceding claim in which the detergent composition is wrapped in a flow-wrap sealed polymer-based packaging system.

10

15. The combination substantially as hereinbefore described with reference to the accompanying examples.

15

16. A process for preparing a packaged detergent composition comprising the steps of:-

20

- placing at least on tablet of compacted particulate detergent composition in a packaging system having a moisture vapour transmission rate of less than 20 g/m²/24 hours;
- sealing the packaging system; and
- storing the thus formed sealed packaged detergent composition for at least 24 hours.

25

INTERNATIONAL SEARCH REPORT

national Application No
PCT/EP 98/01274

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C11D17/00 C11D17/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C11D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 634 485 A (THE PROCTER & GAMBLE COMPANY) 18 January 1995 see page 18, line 1 - line 11 see page 19, line 28 - line 31 & WO 95 02681 A cited in the application & EP 0 634 484 A ---	1, 10
A	WO 95 18215 A (ECOLAB INC.) 6 July 1995 cited in the application see page 19, line 4 - page 20, line 28 see page 4, line 33 - page 6, line 32 see page 15, line 11 - page 19, line 2 see examples --- -/--	1

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

19 June 1998

Date of mailing of the international search report

06/07/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

Ketterer, M

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 98/01274

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 92 20775 A (ECOLAB INC.) 26 November 1992 see working examples 3,5,6 see claims ---	1,2,10
A	EP 0 467 481 A (SARA LEE /DE N.V.) 22 January 1992 see claims 1,7; examples ---	1,10-12
A	WO 92 06163 A (THE PROCTER & GAMBLE COMPANY) 16 April 1992 see page 33, line 16 - page 34, line 25 see claim 1; examples -----	1,10

Form PCT/ISA/210 (continuation of second sheet) (July 1992)

page 2 of 2

INTERNATIONAL SEARCH REPORT

national Application No
PCT/EP 98/01274

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 634485 A	18-01-1995	EP 0634484 A	18-01-1995
		AU 7220794 A	13-02-1995
		BR 9407273 A	01-10-1996
		CZ 9503412 A	11-09-1996
		HU 73039 A	28-06-1996
		JP 9500170 T	07-01-1997
		WO 9502681 A	26-01-1995
		AU 7258294 A	13-02-1995
		BR 9407274 A	01-10-1996
		CN 1129952 A	28-08-1996
		CZ 9503404 A	12-06-1996
		HU 73058 A	28-06-1996
		JP 9502742 T	18-03-1997
		WO 9502677 A	26-01-1995
		ZA 9405771 A	23-03-1995
WO 9518215 A	06-07-1995	AU 684596 B	18-12-1997
		AU 1443495 A	17-07-1995
		BR 9407783 A	11-03-1997
		EP 0737245 A	16-10-1996
		JP 9507263 T	22-07-1997
		NZ 278258 A	22-09-1997
		US 5759988 A	02-06-1998
		ZA 9410377 A	01-07-1996
WO 9220775 A	26-11-1992	US 5316688 A	31-05-1994
		AT 125565 T	15-08-1995
		AU 659848 B	01-06-1995
		AU 2016292 A	30-12-1992
		CA 2104880 A	15-11-1992
		DE 69203721 D	31-08-1995
		DE 69203721 T	11-01-1996
		DK 585352 T	27-12-1995
		EP 0585352 A	09-03-1994
		ES 2078049 T	01-12-1995
		JP 6507667 T	01-09-1994
		MX 9202257 A	01-08-1993
		NZ 242699 A	22-12-1994
EP 467481 A	22-01-1992	NL 9001651 A	17-02-1992

INTERNATIONAL SEARCH REPORT

national Application No
PCT/EP 98/01274

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 467481 A		AT 121772 T AU 651602 B AU 8113191 A DE 69109200 D DK 467481 T JP 4226600 A	15-05-1995 28-07-1994 23-01-1992 01-06-1995 17-07-1995 17-08-1992
WO 9206163 A	16-04-1992	AU 8714891 A CA 2093438 A,C CN 1061433 A CZ 9300595 A EP 0591203 A FI 931526 A HU 64388 A JP 6501973 T NZ 240124 A PT 99158 A SK 31093 A US 5482642 A	28-04-1992 07-04-1992 27-05-1992 15-06-1994 13-04-1994 02-06-1993 28-12-1993 03-03-1994 27-06-1995 30-09-1992 12-01-1994 09-01-1996

Form PCT/ISA/210 (patent family annex) (July 1992)